

Publishable Summary for 20FUN05 SEQUME

Single- and entangled photon sources for quantum metrology

Overview

Quantum technologies (QT) are one of the most relevant contributors to innovation and advanced technologies. However, there is an important range of quantum-enhanced measurements that are not yet exploited by national metrology institutes (NMIs) because single-photon and entangled-photon sources with the required performance parameters (e.g. purity for single-photon sources and sub-shot noise quantification for entangled sources), are not readily available. Major advancements have been made in engineering these sources, but if they are to be used in metrological applications, significant further development is necessary. This project will develop high brightness, high-efficiency entangled photon sources (based on semiconductor quantum dots (QDs)) and it will exploit high-purity single-photon sources (based on ion implantation in diamond and on single molecules), to demonstrate the quantum advantage achieved when using these sources for specific measurements.

Need

Several international, European and national quantum programmes are currently under way, e.g. the European “Quantum-Flagship”, Quant-ERA, ITN Networks, the German QT initiatives, the UK Quantum Technologies programme (which was recently re-launched), as well as programmes in Australia, Austria, Canada, China, Japan, Russia, Switzerland, and in the US. However, these initiatives do not yet comprehensively address the metrological challenges related to QT, such as traceability, standardisation and optimisation of quantum enhanced measurements. A robust European metrology infrastructure is required that enables the traceable characterisation of entangled-photon and single-photon sources (SPSs).

The Strategic Research Agenda for Metrology in Europe has identified a need for further work in quantum metrology, to ensure Europe keeps at the leading edge of QT development worldwide. Noise limits must be overcome and the invasiveness of measurements (i.e. disturbance on the tested objects) must be minimised, both of which can be achieved using novel quantum-enhanced approaches. For this, single-photon sources and entangled-photon sources used in traceable quantum-enhanced measurements must be assessed and their performance parameters specified. Additionally, novel validated methods should be developed for the fabrication of single-photon sources and to optimise the sources for highest purity and indistinguishability.

Objectives

The overall objective of the project is to develop bright entangled photon sources based on different application-oriented platforms and to exploit high-purity single-photon sources to demonstrate the quantum advantage achievable using these sources for specific measurements.

The specific objectives of the project are:

1. To assess single-photon sources and entangled-photon sources in traceable quantum-enhanced measurements (e.g. quantum calibration at the single-photon level, sub-shot noise measurements, quantum imaging, sub-diffraction imaging and quantum illumination), to overcome classical measurement limits (e.g. noise);
2. To specify the performance parameters of single-photon and entangled-photon sources required to carry out different quantum-enhanced measurements;
3. To develop novel validated methods for the fabrication of single-photon sources and to optimise the sources for highest purity ($g^{(2)}(t=0)$ close to 0), brightness (photon rate $> 5 \times 10^6$ photons per second) and indistinguishability (Hong-Ou-Mandel visibility $> 95\%$), according to the performance parameters specified in Objective 2;
4. To develop the European metrology infrastructure required for the traceable characterisation of entangled-photon and single-photon sources, i.e. detectors (including photon-number resolving

detectors), amplifiers, as well as standardised quantum-optical setups for characterisation (in particular entanglement tomography);

5. To facilitate the take up of the technology and measurement infrastructure developed in the project by the EMN Quantum, measurement supply chain, standards developing organisations (e.g. CEN and ISO) and end users (in the fields of quantum technology and nano-photonics).

Progress beyond the state of the art

This project will partially build on previous achievements of EMRP EXL02 SIQUTE and EMPIR 17FUN06 SIQUST projects and is going beyond the state of the art by developing optimised single- and entangled-photon sources for quantum metrological application and by demonstrating the quantum advantage achieved by using these sources.

Assessment of single-photon sources and entangled-photon sources in traceable quantum-enhanced measurements (objective 1)

This project is investigating new fields of quantum metrology and quantum-enhanced measurements, which have not been investigated thus far. In particular, the project is carrying out a metrological assessment of SPSs and entangled-photon sources in traceable, quantum-enhanced measurements, e.g., quantum calibration at the single-photon level, sub-shot noise measurements, quantum imaging, sub-diffraction imaging and quantum illumination, to overcome classical measurement limits (e.g. noise). To achieve these measurements, the project is designing, developing and implementing high performance single-photon and entangled-photon light sources for applications in enhanced quantum imaging with the target of beating the quantum noise limit. New paradigms of quantum measurements, such as weak values (i.e., the amount of correlation between measured and measuring system) and correlated measurements in Hong-Ou-Mandel (HOM) configurations are explored as a tool for enhancing the resolution and sensitivity of microscopes and spectroscopic tools. Furthermore, the NMI is addressing the completely new aspect of traceability in quantum enhanced measurements.

A mid-infrared (MIR) microscope based on heralded single photons for the exploitation of quantum interference was established. Measurements on polystyrene and biological samples, such as thin tissue samples and bacteria samples have started, in which heralded single MIR photons will be used for imaging of specific biomarkers (lipids, water).

Traceable calibration of the absolute responsivity of a reference analogue low-noise detector has been performed. Moreover, to improve the photon flux extraction of single-photon emitters based on a single molecule, different methods for modelling and optimising nanophotonic structures incorporating point-like single-photon emitters have been developed. The calibration of a SPAD has been performed exploiting the high purity single photon flux obtained from two different molecule-based SPSs under pulsed operation. The calibration is based on a direct comparison of the signal obtained from the SPAD and the output of the reference analogue low-noise detector in different conditions of intensity and repetition rate. The evaluation of the results of the measurements is currently under way.

Performance parameters of single-photon and entangled-photon sources (objective 2)

This project is improving the performance parameters (e.g., purity and sub-shot noise quantification) for quantum light sources. The main thrust of this project, however, is to explicitly determine the performance parameters, which are necessary for different quantum-enhanced measurements. This will be achieved by identifying both consolidated and recently proposed tools and physical observables, suitable for characterising the relevant “quantumness” properties, such as e.g., entanglement verification, sub-shot noise quantification, squeezing measurements for entangled sources; and purity, Glauber correlation functions, and photon flux variance measurements for SPSs.

A theoretical model for the emission dynamics of a solid-state single-photon source has been developed for pulsed and continuous wave (CW) emission, the investigation of the properties and features of $g^{(n)}$ and $\Theta^{(n)}$ parameters for mode reconstruction in sources assessment has started and is being validated against experimental datasets. The project used a QD-based single-photon source to drive the biexciton-exciton emission cascade resonantly and to investigate the impact of experimental parameters on the non-classical performance of this quantum light source; results show that dephasing of the biexciton and exciton states, spectral blinking, occupation of excitonic dark states and uncorrelated background photons are limiting factors for the visibility of the source. Moreover, the project has developed a SPDC model for different types of

nonlinear crystal materials, considering the non-ideality of the relevant experimental parameters. Finite-element modelling of a waveguide-integrated photonic cavity has been performed, and a surrogate model trained via machine learning algorithm has been developed to provide quantitative estimates of sensitivities to fabrication tolerances.

Von Neumann entropy (noise measure) is estimated using tools of quantum information, and the noise measure mean value and uncertainty is determined via Shannon entropy for random variable derived by orthogonal POVM measurements. The experimental key parameters for carrying out different quantum enhanced measurements were assessed. The total outcoupling efficiency of the channel has been identified as the major limitation for the achievement of substantial quantum advantage in several protocols. The quantum enhanced methods not relying on outcoupling efficiency, and more in general on detection efficiency, such as those based on Glauber's functions, are identified as the most robust and loss insensitive.

Development of novel validated methods for the fabrication of single-photon sources and optimisation of the sources (objective 3)

Within this project, the partners are advancing methods for the fabrication of SPSs and optimise the development of sources with the highest purity ($g^{(2)}(t=0)$ close to 0 (i.e. target value < 0.001 in the context of this project), brightness (photon rate $> 5 \times 10^6$ photons per second) and indistinguishability (Hong-Ou-Mandel visibility $> 95\%$). This includes fabrication of i) SPSs based on single defects in bulk diamond and on single molecules, and ii) single and entangled photon sources based on InGaAs/GaAs quantum dots (QDs).

A bulk diamond sample containing single SnV centres was produced and tested delivering promising results, i.e., $g^{(2)}(0) < 0.1$. The emitters are almost strain-free, showing ideal ground state splitting and narrow resonance lines. A charge transition cycle of the SnV, affecting the performance of the centre was identified. A method for charge state stabilisation was found and implemented. A Hong-Ou-Mandel interferometer for determining the single photon indistinguishability of photons from SnV centres was set up with classical visibility of $> 99.5\%$. Furthermore, high-purity single-crystal diamond samples were implanted with alternative ion species for the formation of different emitters at fluences between 10^{10} cm^{-2} - 10^{15} cm^{-2} . The fabrication of solid immersion lenses into the diamond surface has been investigated and an enhancement factor of the photon count rate of 3 - 4 was found, reaching $> 1 \times 10^6$ photons per second in saturation from a single GeV centre.

Single-mesa quantum dot structures and circular Bragg grating (CBG-) structures of high structural quality were fabricated that provide up to 450 kcounts/s under CW excitation in the 910 nm – 930 nm wavelength range. The metamorphic buffer design for the deposition of the InAs telecom QDs on GaAs substrates was modified, leading to samples with narrow linewidth below 40 μeV , a fine-structure splitting below 20 μeV and a single photon purity of 0.005. Using these structures and in-situ lithography, monolithic micro lenses and two-dimensional Bragg cavities ("Bulls-eye" cavities) were fabricated to enhance the brightness of the samples. A fibre coupled single photon rate up to nearly 14 Mcps at a single photon purity of 0.005 was achieved.

A new method using machine-learning mechanism for the iEBL-integration of QD emitters with weak signal-to-noise ratio was developed and applied to increase the position accuracy in the fabrication of the QD emitters.

A new design of photonic structures compatible with electro-optical pumping scheme has been completed. and the fabrication and characterisation of such photonic structures by nondeterministic methods is ongoing.

Development of a European metrology infrastructure for the traceable characterisation of entangled-photon and single-photon sources (objective 4)

This project addresses the traceable characterisation of SPSs and especially of entangled-photon sources with respect to quantum technological applications, which has not yet been achieved. To carry out this traceable characterisation, low-photon flux detectors and corresponding amplifiers, photon-number resolving detectors are being developed, which will go beyond the state-of-the-art in terms of detection noise, measurement uncertainty and stability.

Two photonic integrated circuits (PICs) have been designed, produced, and packaged for 850 nm as six cascaded 1:10 multimode interference (MMI) splitters. Initial tests have been performed showing that the PICs are working as intended. Two fibre-coupled low photon flux detectors for measurement of the splitting ratio up to 6 orders of magnitude attenuation are developed and characterised. Additionally, using a quantum dot source implemented into a 19" housing (including a Stirling cryocooler and fibre-coupled output), fibre-coupling efficiencies of up to 24% in combination with vanishing multi-photon emission were observed.

A set-up for the responsivity calibration of the low-flux photodetector is completed and ready to use.

Results

Assessment of single-photon sources and entangled-photon sources in traceable quantum-enhanced measurements (objective 1)

The single photon purity of our fabricated telecom QDs was evaluated under the non-resonant, quasi-resonant (p-shell) and resonant excitation schemas. The experiments clearly show that p-shell and resonant excitation can be used to produce highly pure single photons with a two-photon probability as low as 0.005 at a record fibre coupled single photon count rate of nearly 14 Mcps.

A single-photon source based on quantum dots was investigated. The wavelength was 927.2 ± 0.1 nm, the photon flux rate was 17.19 ± 0.09 Mphotons/s (corresponding to (3.68 ± 0.02) pW) and the total efficiency of the source was 21.65 ± 0.16 %, while maintaining a high single-photon purity, indicated by a $g^{(2)}(t=0)$ value of approx. 0.03. This is one of the brightest SPSs reported on so far with a high single-photon purity.

A Franson-interferometer has been developed and is in use. A QD-based single-photon source was used to drive the biexciton-exciton emission cascade by two-photon resonant excitation. Our results show that for low excitation powers, the Franson-Visibility reaches 70 % which clearly exceeds the classical limit of 50 % and proves the violation of Bell's inequality. In addition, further optimisation of the Franson-interferometer was performed, including its extension with an active laser-stabilisation mechanism for highly reliable operation. This will enable to operate it in a "hugged" configuration and eliminate loopholes. The existing results will be refined with this advanced setup.

The characterisation of the mid infrared source emission spectrum and emission wavelengths of the entangled photons generated by spontaneous parametric down-conversion (SPDC) were carried out. In order to gain insight into the quantum advantage gained by excitation with MIR/NIR entangled beam, the microscope for conducting low flux illumination of polystyrene samples was set up. The SPDC source is being investigated with respect to its usefulness for two photon absorption measurements.

A Quantum Interference Imaging Mid-IR system for biological samples has been set up, and low flux illumination of polystyrene samples is being conducted to gain insight into the quantum advantage gained by excitation with a MIR/NIR entangled beam. Furthermore, the microscope is being tested for losses, collection rate, scanning speed and spatial resolution. Also, traceability is being investigated for the Quantum Interference Imaging Mid-IR system.

Performance parameters of single-photon and entangled-photon sources (objective 2)

A theoretical model for the emission dynamics of a solid-state single-photon source has been developed, including continuous wave (CW) and pulsed excitation and emission. Second- and higher-order Glauber ($g(n)$) and theta ($\Theta(n)$) parameters were identified as complementary suitable tools for the qualification of non-classical photon emission. The investigation in the properties and features of $g(n)$ and $Q(n)$ parameters for sources assessment has started. A theoretical model was developed to exploit a combination of both parameters for source mode reconstruction. The model has been validated against available experimental data sets. An article will soon be submitted for peer review.

Models of quantum dot based SPSs have been developed, parameter optimization in order to maximise Purcell factor and extraction has been performed. Different designs for vertical extraction have been compared in terms of their performance, designs for on-chip extraction have been optimised, designs with multiple, interfering resonances have been investigated. Modelling and optimisation methods and scripts have been made available in an open access data publication (Zenodo 6565850, 2022).

The respective experimental key parameters of entangled photon sources that need to be measured to assess their non-classicality performances were collected. Among them are intrinsic parameters (generation probability / rate of two-photon state, decay times of biexciton and exciton, entanglement fidelity, fine-structure splitting, spin precession of biexcitonic/excitonic states, and background luminescence) as well as external parameters with noticeable impact on measurement results (photon-extraction efficiency of the device under test (DUT), temporal resolution and efficiency of detectors, and dark counts / noise of detection system). The setup for quantum state tomography including two-photon resonant excitation is ready to use.

A SPDC model for different types of nonlinear crystal materials has been developed based on SPDC Green functions. The model considers experimental parameters, such as nonlinearity, phase-matching condition, losses, crystal type. The parameters to be calculated are flux rate, joint spectral amplitude, purity of the generated photon pairs.

A waveguide-integrated photonic cavity has been investigated using finite-element modelling. A surrogate

model, trained with a machine learning algorithm (Bayesian optimisation) has been developed and used to provide quantitative estimates of sensitivities to fabrication tolerances. A method for design optimisation of emitter-to-fibre coupling, considering the impact of fabrication tolerances, has been developed and applied. Furthermore, models for studying impact of NV-centre placement and polarization in diamond nano-resonators on optical properties of emitted single photons have been developed and applied for analysing experimental results. Scripts and data for modelling these systems have been made available in an open access data publication.

A QD-based single-photon source was used to drive the biexciton-exciton emission cascade resonantly and to investigate the impact of experimental parameters on the non-classical performance of this quantum light source. It was shown that dephasing of the biexciton and exciton states have a severe impact on the visibility which is reduced below 50 % when the coherence time drops below 300 ps. It was also found that deviations from the ideal and undisturbed biexciton-exciton transition due to spectral blinking and the occupation of excitonic dark states as well as uncorrelated background photons limits the visibility as well. These are experimentally accessible key parameters to assess the non-classicality performance.

Development of novel validated methods for the fabrication of single-photon sources and optimisation of the sources (objective 3)

Single SnV centres were identified and tested, and pure single photon emission was detected with a $g^{(2)}(0)$ -value < 0.1 , where the deviation from zero is entirely due to detector dark counts (noise limit $g^{(2)}(0) = 0.093$). The emitters are almost strain-free, showing ideal ground state splitting and narrow resonance lines, when annealed at 2100°C and 8 GPa. The charge transition cycle of the SnV was identified and used to devise a method for charge state stabilization, i.e., by illumination with a laser in the blue spectral range. The charge state can be initialized and results in very narrow photoluminescence excitation lines for over 1 hour of experiment, i.e., the cumulative linewidth is 33 MHz at a Fourier-limit of 25 MHz. A Hong-Ou-Mandel interferometer for determining the single photon indistinguishability was set up with a classical visibility of > 99.5 %. Furthermore, high-purity single-crystal diamond samples were implanted with alternative ion species for the formation of different emitters: F, Cl, Fe, O, Mg, Mn, Ar, Ge and Pb at fluences between 10^{10} cm^{-2} - 10^{15} cm^{-2} , followed by post-implantation annealing (temperature: 900 °C - 1200 °C).

The photophysics of the SnV- centre was explored in detail. A rate equation model is proposed that includes the optical ionisation process to the dark SnV(2-) state and is applied to an extensive set of measurements on different SnV centres, along with a thorough characterisation of the efficiency of the measurement setup. It was concluded that a charge-stabilised SnV- centre is a nearly ideal single photon source in terms of quantum efficiency, since one can describe any reduced photon rate by ionization to the optically inactive SnV(2-) charge state without assuming other non-radiative decay channels.

Single-mesa quantum dot structures and circular Bragg grating (CBG-) structures of high structural quality are fabricated that provide up to 450 kcounts/s under CW excitation in the 910 nm – 930 nm wavelength range. The metamorphic buffer design for the deposition of the InAs telecom QDs on GaAs substrates was modified in such a way that single-lambda cavities can be built around selected QDs. With this approach, samples were fabricated and evaluated which exhibit narrow linewidth of below 40 μeV , a fine-structure splitting below 20 μeV and a single photon purity as low as 0.005. With these structures and applying in-situ lithography, monolithic micro lenses and two-dimensional Bragg cavities (“Bulls-eye” cavities) were fabricated to enhance the brightness of the samples. A fibre coupled single photon rate up to nearly 14 Mcps at a single photon purity of 0.005 was achieved. This is at the moment worldwide the highest count rate value of a semiconductor quantum dot emitting in the telecom C-band.

Methods for modelling and optimising nanophotonic structures incorporating point-like single-photon emitters have been developed. This includes circular Bragg gratings as high-Q resonators, and their coupling to fibres. Data and parameterised modelling scripts have been made available as open-access data publications to allow for a straight-forward application to all material and source systems of this resonator class (Zenodo 7360516, 2022).

Development of a European metrology infrastructure for the traceable characterisation of entangled-photon and single-photon sources (objective 4)

The first transition edge sensors (TES), composed of Au/Ti and optimised for detection at 1550 nm (0,8 eV) were integrated in the cryo-optic facility and successfully characterised in terms of system detection efficiency, response speed and energy resolution. For one of the devices a record detection efficiency around 98 % was

observed along with a minimum energy resolution of around 0.45 eV and a signal decay time of less than 170 ns.

Two photonic integrated circuits (PICs), i.e., six cascaded 1:10 multimode interference splitters, have been designed, produced, packaged and tested at 850 nm. It has been shown that cascading the two PICs can also be made to achieve higher split ratios than 1:10⁶ and down to 1:10¹⁰. A portable predictable low photon flux (few fW) calibration facility was developed, with a high splitting ratio PIC implemented.

A new front-end electronic, based on switched integrator principle, has been designed, manufactured, and assembled. The new amplifier has dual channel capabilities that will be used to measure split ratios of up to 1:10⁶ by measuring the photocurrent of two fiber coupled photodiodes simultaneously.

Two low noise low photon flux fibre coupled detectors have been constructed for a splitting ratio of up to 1:10⁶. Their responsivity has been calibrated in the spectral range from 580 nm to 970 nm traceable to the primary standard for optical power, the cryogenic radiometer. Preliminary tests performed on a fibre coupled quantum dot single photon source emitting at 933 nm showed measurement of photon flux as low as 4×10^5 photons/s with noise at the level of 1 %.

For the portable semiconductor quantum dot system, the supporting system (19" housing including a Stirling cryocooler and fibre-coupled output) is ready to use. First tests were performed based on a free-space as well as a fibre-based configuration. Fibre-coupling efficiencies of up to 24 % in combination with vanishing multiphoton emission event was observed. For the room temperature portable source, suitable samples were identified and investigated showing count rates exceeding 10⁶ counts/s.

A set-up has been developed, which is based on confocal measurement system with Time-Correlated-Single-Photon-Counting capability for calibration of detectors by using SPSs. The tracking of photons emitted by a source is realised using Hanbury Brown and Twiss interferometer configuration in conjunction with multichannel event timer electronics. The measurement system is capable of inserting radiation from either excited SPSs, by using lasers of measurement system, or from externally coupled transportable SPSs. The optical output of the measurement system to DUT is either open-space or fibre-coupled.

Impact

The project webpage was created (<https://sequme.cmi.cz/>) and has had more than 5000 views so far. In the first 27 months of the project, 58 presentations were given at conferences, seminars and workshops. Additionally, 29 papers have been published in open access peer-reviewed journals. The consortium has further delivered 3 external and 4 internal training activities. The external trainings dealt with the fabrication and characterisation of quantum dots in semiconductor structures, with deterministic ion implantation topics and with the detection of entangled photons from spontaneous parametric down-conversion sources. These trainings were predominantly for the scientific community.

Impact on industrial and other user communities

This project will trigger and accelerate progress in the field of quantum technologies, due to the development of high-end, highly innovative quantum devices for use and application in science, quantum communication and quantum metrology. More specifically, the entangled and single-photon sources will impact the development of the associated measurement infrastructure for quantum enhanced metrology and for low-flux measurements, i.e., new and better amplifiers, new optical single photon excitation sources, which e.g., can be used in different fields where low optical fluxes need to be measured. The developed sources have the potential to become a commercial product useful for companies active in the field of quantum technology. They will also be very useful for educational purposes, both in academia and schools. This will be achieved through academic partners, and demonstrations at universities and schools. Furthermore, the lack of useful entangled and single-photon sources hinders the development of quantum technology fields such as quantum cryptography and quantum metrology; the developments within this project with respect to higher single photon flux rates, photon indistinguishability and entanglement, will remove these roadblocks. To support knowledge transfer to the industrial community, a workshop on the newly developed devices will be organised and held to which representatives of industry (both manufacturers of and users of photon sources) will be invited.

Impact on the metrology and scientific communities

This project will have high impact on the metrology and scientific communities through the development of entangled and single-photon sources, based on single emitters. Specifically, the knowledge about entangled photon sources and their use at NMIs are scarce and therefore opportunities for applications with quantum

light sources have not been exploited so far. It is anticipated that this project will create rather fast, new prospects and applications for quantum enhanced metrology, e.g., sub-shot noise metrology, quantum imaging of biological systems and quantum illumination. In addition, the project will further accelerate the development of a characterisation infrastructure for low flux measurements, e.g., in new amplifiers, as well as in practical fibre-coupled single-photon sources, where low optical fluxes need to be measured.

The project partners are members of the EMN Quantum are presenting the project and its results to this network and its corresponding network project. The results of this project are being disseminated to the scientific community predominantly via high impact publications on sources of single, indistinguishable and entangled photons, low flux and single-photon radiometry, low-noise amplifiers and excitation sources, therefore paving the way new and unforeseen research fields. To further support knowledge transfer, representatives of academic organisations and NMIs will be invited to a workshop that the project will organise.

Within the project, a software to simulate the performances of TES detectors were developed, available under <https://tes.inrim.it/>.

Impact on relevant standards

New documentary standards based on the results of this project in the field of low-flux radiometry are expected, as a result of input to different standardisation bodies. The current *mise en pratique* for the candela allows the photon-number-based (and thus quantum-based) realisation of photometric and radiometric units. Furthermore, in the long term, a photon-based definition of the SI base quantity candela might be envisaged. Members of the consortium are active in the European Telecommunications Standards Institute (ETSI) and in CEN-CENELEC with respect to standardisation in (quantum) communication and in quantum technology, respectively. Results from this project will be implemented in documentary standards generated by these standards developing organisations. In the first 27 months of the project, new standards for quantum key distribution have been drafted, i.e., ETSI GS QKD 013 entitled “Characterization of assembled QKD transmitter and receiver modules” and “RGS/QKD-016ed2_PP (GS QKD 016) - Protection Profile v211”, which will take up results from the project especially with respect to single-photon sources. In CEN/CENELEC, the Focus Group on Quantum Technologies (FGQT) compiled a roadmap including sections on single- and entangled photon sources and on single-photon detectors (“Standardization Roadmap on Quantum Technologies”). The work led to the formation of a Joint TC on quantum technologies (CEN/CENELEC JTC22), where experts from the partners will participate.

Longer-term economic, social and environmental impacts

The project has the potential to have a significant economic impact on the European market, because it will strengthen Europe’s position in the field of quantum technologies. The sources and metrological infrastructure developed within the project may lead to their implementation in commercial products and the development of highly innovative commercial devices, respectively, and thus stimulate new high-tech jobs in Europe. This project may also have a long-term impact on the field of data safety, guaranteed by secure quantum communication, for which single-photon sources can be exploited.

List of publications

1. L. Bremer, C. Jimenez, S. Thiele, K. Weber, T. Huber, S. Rodt, A. Herkommer, S. Burger, S. Höfling, H. Giessen, S. Reitzenstein, Numerical optimization of single-mode fiber-coupled single-photon sources based on semiconductor quantum dots, *Opt. Express* 30, 15913-15928 (2022). <https://doi.org/10.1364/OE.456777>
2. Klenovský, P., Baranowski, P., Wojnar, P., Excitonic fine structure of epitaxial Cd(Se,Te) on ZnTe type-II quantum dots, *Physical Review B* 105 (2022) 195403. <https://doi.org/10.1103/PhysRevB.105.195403>
3. Klenovský, P., Valdhans, J., Krejčí, L., Valtr, M., Klapetek, P. and Fedotova, O., Interplay between multipole expansion of exchange interaction and Coulomb correlation of exciton in colloidal II–VI quantum dots, *Electronic Structure* 4 (2022) , 015006, <https://doi.org/10.1088/2516-1075/ac5b7e>
4. Marletto, C., Vedral, V., Knoll, L.T., Piacentini, F., Bernardi, E., Rebufello, E., Avella, A., Gramegna, M., Degiovanni, I.P., and Genovese, M., Emergence of Constructor-Based Irreversibility in Quantum Systems: Theory and Experiment, *Physical Review Letters* 128 (2022), 080401, <https://doi.org/10.1103/PhysRevLett.128.080401>

5. Steindl, P. and Klenovský, P., Dimension-Dependent Phenomenological Model of Excitonic Electric Dipole in InGaAs Quantum Dots, *Nanomaterials* 12 (2022), 719, <https://doi.org/10.3390/nano12040719>
6. Mittelstädt, A., Schliwa, A. and Klenovský, P., Modeling electronic and optical properties of III–V quantum dots—selected recent developments, *Light: Science & Applications* 11 (2022), 17, <https://doi.org/10.1038/s41377-021-00700-9>
7. Corte, E., Sachero, S., Ditalia Tchernij, S., Lühmann, T., Pezzagna, S., Traina, P., Degiovanni, I.P., Moreva, E., Olivero, P., Meijer, J., Genovese, M. and Forneris, J. (2022), Spectral Emission Dependence of Tin-Vacancy Centers in Diamond from Thermal Processing and Chemical Functionalization. *Adv. Photonics Res.*, 3: 2100148. <https://doi.org/10.1002/adpr.202100148>
8. S. Ditalia Tchernij, E. Corte, T. Lühmann, P. Traina, S. Pezzagna, I. P. Degiovanni, G. Provas, E. Moreva, J. Meijer, P. Olivero, M. Genovese and J. Forneris, Spectral features of Pb-related color centers in diamond – a systematic photoluminescence characterization, *New J. Phys.* 23 063032 (2021), <https://doi.org/10.1088/1367-2630/ac038a>
9. S. Kück, M. López, H. Hofer, H. Georgieva, J. Christinck, B. Rodiek, G. Porrovecchio, M. Šmid, S. Götzinger, C. Becher, P. Fuchs, P. Lombardi, C. Toninelli, M. Trapuzzano, M. Colautti, G. Margheri, I. P. Degiovanni, P. Traina, S. Rodt, S. Reitzenstein, Single photon sources for quantum radiometry: a brief review about the current state-of-the-art. *Appl. Phys. B* 128, 28 (2022). <https://doi.org/10.1007/s00340-021-07734-2>
10. Volkova, K.; Heupel, J.; Trofimov, S.; Betz, F.; Colom, R.; MacQueen, R.W.; Akhundzada, S.; Reginka, M.; Ehresmann, A.; Reithmaier, J.P.; Burger, S.; Popov, C.; Naydenov, B. Optical and Spin Properties of NV Center Ensembles in Diamond Nano-Pillars. *Nanomaterials* 12, 1516 (2022). <https://doi.org/10.3390/nano12091516>
11. R. Colom, F. Binkowski, F. Betz, Y. Kivshar, S. Burger, Enhanced Purcell factor for nanoantennas supporting interfering resonances, *Phys. Rev. Research* 4, 023189, <https://doi.org/10.1103/PhysRevResearch.4.023189>
12. Y. J. Wang, L. Vannucci, S. Burger, N. Gregersen, Near-unity efficiency in ridge waveguide-based, on-chip single-photon sources, *Mater. Quantum Technol.* 2, 045004 (2022). <https://doi.org/10.1088/2633-4356/aca8e8>
13. Sittig, R., Nawrath, C., Kolatschek, S., Bauer, S., Schaber, R., Huang, J., Vijayan, P., Pruy, P., Portalupi, S. L., Jetter, M. and Michler, P., "Thin-film InGaAs metamorphic buffer for telecom C-band InAs quantum dots and optical resonators on GaAs platform" *Nanophotonics*, vol. 11, no. 6, 2022, pp. 1109-1116. <https://doi.org/10.1515/nanoph-2021-0552>
14. Guimbao, J.; Sanchis, L.; Weituschat, L.M.; Llorens, J.M.; Postigo, P.A. Perfect Photon Indistinguishability from a Set of Dissipative Quantum Emitters. *Nanomaterials* 2022, 12, 2800. <https://doi.org/10.3390/nano12162800>
15. Görlitz, J., Herrmann, D., Fuchs, P. et al. Coherence of a charge stabilised tin-vacancy spin in diamond. *npj Quantum Inf* 8, 45 (2022). <https://doi.org/10.1038/s41534-022-00552-0>
16. L. Bremer, S. Rodt, S. Reitzenstein, Fiber-coupled quantum light sources based on solid-state quantum emitters, *Mater. Quantum Technol.* 2 042002. <https://doi.org/10.1088/2633-4356/aca3f3>
17. S. M. F. Raupach, I. P. Degiovanni, H. Georgieva, A. Meda, H. Hofer, M. Gramegna, M. Genovese, S. Kück, M. López, Detection rate dependence of the inherent detection efficiency in single-photon detectors based on avalanche diodes, *Phys. Rev. A* 105, 042615. <https://doi.org/10.1103/PhysRevA.105.042615>
18. L. Rickert, F. Betz, M. Plock, S. Burger, T. Heindel, High-performance designs for fiber-pigtailed quantum-light sources based on quantum dots in electrically-controlled circular Bragg gratings. *Opt. Express* 31, 14750 (2023). <https://doi.org/10.1364/OE.486060>
19. L. Kuen, F. Betz, F. Binkowski, P.-I. Schneider, M. Hammerschmidt, N. Heermeier, S. Rodt, S. Reitzenstein, S. Burger. Applying a Riesz-projection-based contour integral eigenvalue solver to

- compute resonance modes of a VCSEL. *Proc. SPIE* 12575, 125750J (2023). <http://arxiv.org/abs/2306.02926>
20. C. Nawrath, R. Joos, S. Kolatschek, S. Bauer, P. Pruy, F. Hornung, J. Fischer, J. Huang, P. Vijayan, R. Sittig, M. Jetter, S. L. Portalupi, and P. Michler, Bright Source of Purcell-Enhanced, Triggered, Single Photons in the Telecom C-Band, *Adv Quantum Technol.* 2023, 2300111. <https://doi.org/10.1002/qute.202300111>
 21. M. Hohn, K. Barkemeyer, M. von Helversen, L. Bremer, M. Gschrey, J.-H. Schulze, A. Strittmatter, A. Carmele, S. Rodt, S. Bounouar, and S. Reitzenstein, Energy-time entanglement from a resonantly driven quantum-dot three-level system, *Phys. Rev. Research* 5, L022060 (2023), <https://doi.org/10.1103/PhysRevResearch.5.L022060>
 22. G. Murtaza, M. Colautti, M. Hilke, P. Lombardi, F. Cataliotti, A. Zavatta, D. Bacco, and C. Toninelli, "Efficient room-temperature molecular single-photon sources for quantum key distribution," *Opt. Express* 31, 9437-9447 (2023). <https://doi.org/10.1364/OE.476440>
 23. J. Christinck, F. Hirt, H. Hofer, Z. Liu, M. Etzkorn, T. Dunatov, M. Jakšić, J. Forneris, S. Kück; Bright single-photon emission from a GeV center in diamond under a microfabricated solid immersion lens at room temperature. *J. Appl. Phys.* 21 May 2023; 133 (19): 193102. <https://doi.org/10.1063/5.0150208>
 24. R. Duquennoy, M. Colautti, R. Emadi, P. Majumder, P. Lombardi, and C. Toninelli, "Real-time two-photon interference from distinct molecules on the same chip," *Optica* 9, 731-737 (2022). <https://doi.org/10.1364/OPTICA.452317>
 25. X. Yuan, S. F. Covre da Silva, D. Csontosová, H. Huang, C. Schimpf, M. Reindl, J. Lu, Z. Ni, A. Rastelli, P. Klenovský, "GaAs quantum dots under quasiuniaxial stress: Experiment and theory", *Phys. Rev. B* 107, 235412 (2023). <https://doi.org/10.1103/PhysRevB.107.235412>
 26. Nieto Hernández, E., Redolfi, E., Stella, C., Andrini, G., Corte, E., Sachero, S., Ditalia Tchernij, S., Picariello, F., Herzig, T., Borzdov, Y. M., Kupriyanov, I. N., Kubanek, A., Olivero, P., Meijer, J., Traina, P., Palyanov, Y. N., Forneris, J., Efficiency Optimization of Ge-V Quantum Emitters in Single-Crystal Diamond upon Ion Implantation and HPHT Annealing. *Adv Quantum Technol.* 2023, 6, 2300010. <https://doi.org/10.1002/qute.202300010>
 27. J. M. Llorens, B. Alén, "Inverse Design of a Hybrid Mie-Tamm Photonic Structure as a Highly Directional Gigahertz Single-Photon Source", *Phys. Rev. Applied* 19, 034054. <https://doi.org/10.1103/PhysRevApplied.19.034054>
 28. E. Corte et al., "Magnesium-Vacancy Optical Centers in Diamond", *ACS Photonics* 2023, 10, 1, 101–110, <https://arxiv.org/abs/2206.08670>
 29. Petr Steindl et al., "On the importance of antimony for temporal evolution of emission from self-assembled (InGa) (AsSb)/GaAs quantum dots on GaP(001)", 2021, *New J. Phys.* 23 103029 <https://doi.org/10.1088/1367-2630/ac2bd6>

This list is also available here: <https://www.euramet.org/repository/research-publications-repository-link/>

Project start date and duration:		1 June 2021, 36 months
Coordinator: Stefan Kück, PTB		Tel: +49 531 592 4010
Project website address: https://sequme.cmi.cz/		E-mail: stefan.kueck@ptb.de
Internal Funded Partners:	External Funded Partners:	Unfunded Partners:
<ol style="list-style-type: none"> 1. PTB, Germany 2. Aalto, Finland 3. CMI, Czech Republic 4. DFM, Denmark 5. JV, Norway 6. Metroserf, Estonia 7. TUBITAK, Türkiye 	<ol style="list-style-type: none"> 8. CNR, Italy 9. CSIC, Spain 10. FAU, Germany 11. INFN, Italy 12. KBFI, Estonia 13. TUB, Germany 14. UdS, Germany 15. UNITO, Italy 16. USTUTT, Germany 17. ZIB, Germany 	<ol style="list-style-type: none"> 18. INRIM, Italy
RMG: -		